

PatentWeb  
HomeEdit  
SearchReturn to  
Patent List

Help

☐ Include in patent order**MicroPatent® Worldwide PatSearch:** Record 1 of 1

[no drawing available]

[Family Lookup](#)**JP02038434****FLAME-RETARDING POLYOLEFIN RESIN COMPOSITION****NIPPON UNICAR CO LTD****Inventor(s): ;YOSHIDA MAMORU ;SUYA HACHIROU ;HAYASHI SOJI ;KOSHIYAMA  
TAKAO ;HASHIMOTO SATORU ;HOTTA KATSUHIRO****Application No. 63188179 , Filed 19880729 , Published 19900207****Abstract:**

**PURPOSE:** To obtain the title composition which can give a molding prevented from whitening by mixing a polyolefin resin with  $\text{Mg}(\text{OH})_2$  surface-treated with an aminosilane coupling agent.

**CONSTITUTION:** 100 pts.wt.  $\text{Mg}(\text{OH})_2$  (i) optionally treated with a surfactant and having a mean particle diameter of 0.1–15  $\mu\text{m}$ , desirably, 0.5–3  $\mu\text{m}$ , a specific surface area (BET method) of 1–20  $\text{m}^2/\text{g}$ , desirably, 5–8  $\text{m}^2/\text{g}$  is surface-treated with 0.05–3.0 pts.wt. aminosilane coupling agent (ii) (e.g.,  $\gamma$ -aminopropyltriethoxysilane) to obtain a component (i) surface-treated with component (ii). 100 pts.wt. polyolefin resin (e.g., ethylene/ethyl acrylate copolymer) is mixed with 50–300 pts.wt. desirably, 70–170 pts. wt. said component (i).

**COPYRIGHT: (C)1990,JPO&Japio****Int'l Class: C08L02302 C08K00322 C08K00906 C09K02102 C09K02106 C09K02114****MicroPatent Reference Number: 000804770****COPYRIGHT: (C) JPO**PatentWeb  
HomeEdit  
SearchReturn to  
Patent List

Help

---

For further information, please contact:  
[Technical Support](#) | [Billing](#) | [Sales](#) | [General Information](#)